

Board Material

Polyurethane Board for Modeling

Key Properties

- Fine surface structure
- Easily shaped and machined
- Low coefficient of thermal expansion
- Good dimensional stability

Applications

- Master models
- Cubing models
- Patterns

Mechanical Properties

| | | | MB-0670 |
|----------------------------------|-------------|--|-------------------------|
| Color | visual | | Brown |
| Density | ASTM D-792 | g/cm ³ (lb/ft ³) | ca. 0.67 (ca. 41.8) |
| Shore hardness D | ASTM D-2240 | | 60 - 65 |
| Coefficient of thermal expansion | ASTM D-3386 | 10 ⁻⁶ K ⁻⁶ (in/in/°F x 10 ⁻⁶) | 50 - 55 (28 - 31) |
| Deflection temperature, HDT | ASTM D-648 | °C (°F) | 75 - 80 (167 - 176) |
| Compressive strength | ASTM D-695 | MPa (psi) | 15 - 20 (2,200 - 2,900) |
| Flexural strength | ASTM D-790 | MPa (psi) | 20 - 25 (2,900 - 3,600) |

Processing

The product should have a temperature of 20- 25°C (68-77°F) during processing.

Packaging

RAKU® TOOL MB-0670

1500 x 500 x 25 mm
(59.1 x 19.7 x 1.0 in)
1500 x 500 x 50 mm
(59.1 x 19.7 x 2.0 in)
1500 x 500 x 75 mm
(59.1 x 19.7 x 3.0 in)
1500 x 500 x 100 mm
(59.1 x 19.7 x 3.9 in)

Storage

The material should be stored flat and in a dry place. Temperature variations should be avoided during storage and transportation.

Handling Precautions

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.

For information on adhesives and repair pastes see the corresponding individual technical data sheets.