

Board Material

Polyurethane Board for Styling & Design

© RAMPF Tooling Solutions GmbH & Co. KG

PC - Rev.-Status: 02- 2020/05/19

Page 1 of 2

Key Properties

- Light weight and smooth surface
- Easily shaped, minimal dust
- Resistant to organic solvents

Applications

- Design study
- Program proving
- Substructures for Close Contour Paste
- Negative molds for casting

Mechanical Properties

			SB-0160
Color	visual		Light gray
Density	ASTM D-792	g/cm ³ (lb/ft ³)	ca. 0.16 (ca. 10.0)
Glass Transition Temperature, T _g	DSC	°C (°F)	95 – 100 (203 – 212)
Compressive strength	ASTM D-695	MPa (psi)	2 – 3 (290 – 440)
Flexural strength	ASTM D-790	MPa (psi)	2 – 3 (290 – 440)

Processing

The product should have a temperature of 20°C – 25°C during processing.

Packaging

RAKU® TOOL SB-0160

96x24x [2,4,6,8] in

96x48x [1,2,4,6,8,10,12,16] in

Storage

The material should be stored flat and in a dry place. Temperature variations should be avoided during storage and transportation.

Handling Precautions

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.

For information on adhesives and repair pastes see the corresponding individual technical data sheets.