

Board Material

Polyurethane Board for Styling & Design

Key Properties

- Very fine and smooth surface structure
- Easily machined

Applications

- Styling models
- Master models and data control models

Mechanical Properties

			SB-0470
Color	visual		Apricot
Density	ASTM D-792	g/cm ³ (lb/ft ³)	ca. 0.47 (ca. 29.3)
Coefficient of thermal expansion	ASTM D-3386	10 ⁻⁶ K ⁻¹ (in/in/°F x 10 ⁻⁶)	60 – 65 (33 – 36)
Deflection temperature, HDT	ASTM D-648	°C (°F)	75 – 80 (167 – 176)
Glass Transition Temperature, Tg	DSC	°C (°F)	95 – 100 (203 – 212)
Compressive strength	ASTM D-695	MPa (psi)	10 – 15 (1,450 – 2,176)
Flexural strength	ASTM D-790	MPa (psi)	10 – 15 (1,450 – 2,176)

Processing

The product should have a temperature of 20°C – 25°C (68-77°F) during processing.

Packaging

RAKU® TOOL SB-0470	1500 x 500 x 50 mm (59.1 x 19.7 x 2.0 in) 1500 x 500 x 100 mm (59.1 x 19.7 x 3.9 in) 1500 x 500 x 150 mm (59.1 x 19.7 x 5.9 in) 1500 x 500 x 200 mm (59.1 x 19.7 x 7.9 in)
--------------------	---

Storage

The material should be stored flat and in a dry place. Temperature variations should be avoided during storage and transportation.

Handling Precautions

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.

For information on adhesives and repair pastes see the corresponding individual technical data sheets.