

**RAKU-TOOL®**  
**PP-3358 RGIC-600**



**Polyurethane Paste**  
 Adhesive for Working Boards

**Key Properties**

- Good flow and easy application
- Rigid and good adhesion
- RT curing

**Applications**

- Color matched for bonding WB-1258
- Bonding of working boards

**Processing Properties**

			Polyol	Isocyanate
Aspect	visual		Orange	Brown
Mix Ratio		pbw pbv	100 100	50 47
Density	ASTM D-792	g/ml	1.16	1.23
			Mixture	
Pot Life		min	5-8	
Minimal Curing Time @ 77°F (25°C)		hour	4	

**Cured / Mechanical Properties**

			Cure 1	Cure 2
Cure 1:	<b>7 days @ 77°F (25°C)</b>			
Cure 2:	<b>14h @ 104°F (40°C)</b>			
Aspect	visual		Orange	Orange
Density	ASTM D-792	g/ml	1.20	1.20
Density	ASTM D-792	lb/ft <sup>3</sup>	75	75
Shore D Hardness	ASTM D-2240		75-80	75-80
HDT at 66psi	ASTM D-638	°F(°C)	122-131 (50-55)	122-131 (50-55)
Flexural Strength	ASTM D-790	psi	8,350	8,350
Flexural Modulus	ASTM D-790	psi	276,000	276,000
Compressive Strength	ASTM D-695	psi	7,350	7,350
CTE from 77-131°F (25-55°C)	ASTM D-696	10 <sup>-6</sup> /K	80-90	80-90
DSC Tg	ASTM D-7426	°F (°C)	113-122 (45-50)	113-122 (45-50)

**RAKU-TOOL®**  
**PP-3358 RGIC-600**



## **Polyurethane Paste**

### Adhesive for Working Boards

© RAMPF Tooling Solutions GmbH & Co. KG

PK-Rev.-Status: 02 03/09/21

Page 2 of 2

---

#### **Processing**

**The processing and material temperature should be between 68-77°F (20-25°C).** Mix the two components thoroughly in the ratio indicated and apply to both sides of the surface to be bonded.

---

---

#### **Packaging**

Quart Kit	3.3	lbs.	1.5	kg
1 Gal. Kit	13.2	lbs.	6.0	kg

---

---

#### **Storage**

Original containers should be kept tightly sealed and stored at ambient temperatures 59-86°F (15-30°C). If properly stored the products have the shelf-life indicated on the product label. Partly used containers should always be sealed appropriately and used as soon as possible.

---

---

#### **Handling Precautions**

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.

---

RAMPF Group, Inc.  
P.O. Box 930352  
49037 Wixom Tech Dr  
Wixom, MI 48393-2066  
T +1 248.295.0223  
F +1 248.295.0224  
E info@rampf-group.com

[WWW.Rampf-Group.com](http://WWW.Rampf-Group.com)

Our recommendations on the use of the material are based on many years of experience and current scientific and practical knowledge. They are, however, provided without any obligation on our part and do not relieve the buyer of the need for suitability tests. They do not constitute a legal relationship, nor are any protected third party rights whatsoever affected thereby.